

Declared thermal conductivity – ISO13787

EN12667 – measured values

Sample No	Temperature °C	λ [W/mK]
Sample 1	10	0.0428
Sample 2	10	0.0427
Sample 3	10	0.0428
Sample 4	10	0.0424

Sample No	Temperature °C	λ [W/mK]
Sample 1	40	0.0454
Sample 2	40	0.0450
Sample 3	40	0.0454
Sample 4	40	0.0453

Sample No	Temperature °C	λ [W/mK]
Sample 1	20	0.0430
Sample 2	20	0.0427
Sample 3	20	0.0430
Sample 4	20	0.0427

Sample No	Temperature °C	λ [W/mK]
Sample 1	60	0.0484
Sample 2	60	0.0481
Sample 3	60	0.0483
Sample 4	60	0.0483

Declared values

Temperature °C	Declared Thermal conductivity λ W/(mK)
10	0.0433
20	0.0434
40	0.0459
60	0.0487